


# 2" K-13 ON CONCRETE DECK



K-13 ON SOLID BACKING - ASTM C 423							
INCHES	125 hZ	250 hZ	500 hZ	1,000 hZ	2,000 hZ	4,000 hZ	NRC
1"	.11	.32	.84	.99	1.01	.98	.80
2"	.47	.90	1.06	1.06	1.08	1.07	1.00
3"	.57	.99	1.04	1.03	1.00	.98	1.00

All acoustical testing was performed by an NVLAP-accredited laboratory. Testing available on request.



NOTES:




12315 ROBIN BLVD. HOUSTON, TX 77045  
 icc@spray-on.com | 800.444.1252  
 www.spray-on.com