

SonaSpray K-13 Standard Finish

SONASPRAY K-13 STANDARD ON SOLID BACKING

THICKNESS	125 Hz	250 Hz	500 Hz	1,000 Hz	2,000 Hz	4,000 Hz	α_w [-]	NRC
10 mm	0,10	0,20	0,46	0,66	0,78	0,89	0,45	0,55
15 mm	0,17	0,26	0,63	0,85	0,93	0,98	0,55	0,65
20 mm	0,16	0,34	0,74	0,95	0,97	0,94	0,60	0,74
25 mm	0,23	0,49	0,87	0,96	0,97	0,86	0,75	0,80
35 mm	0,26	0,62	1,02	1,07	1,01	0,96	0,90	0,95
45 mm	0,33	0,77	1,12	1,11	1,01	0,93	1,00	1,00

SonaSpray K-13 Special Finish

SONASPRAY K-13 SPECIAL ON SOLID BACKING

THICKNESS	125 Hz	250 Hz	500 Hz	1,000 Hz	2,000 Hz	4,000 Hz	α_w [-]	NRC
10 mm	0,15	0,28	0,59	0,86	0,95	1,02	0,55	0,65
15 mm	0,15	0,33	0,69	0,95	0,98	0,97	0,60	0,75
20 mm	0,16	0,33	0,75	0,96	0,98	0,97	0,60	0,75
25 mm	0,20	0,44	0,89	1,01	0,98	0,93	0,70	0,85

SonaSpray FC Finish

SONASPRAY FC ON SOLID BACKING

THICKNESS	125 Hz	250 Hz	500 Hz	1,000 Hz	2,000 Hz	4,000 Hz	α_w [-]	NRC
10 mm	0,10	0,20	0,48	0,77	0,90	1,00	0,45	0,60
15 mm	0,12	0,25	0,62	0,92	0,98	1,02	0,50	0,70
20 mm	0,17	0,37	0,82	1,04	1,00	0,97	0,65	0,80
25 mm	0,18	0,42	0,88	1,05	0,99	0,97	0,70	0,85

